



PRO-DENSE™ Bone Graft Substitute

Mixing Instructions

150844-2

The following language is included in this packet: English (en)

For additional languages, visit our website www.wright.com
Then click on the Prescribing Use option.

For additional information and translations please contact the manufacturer or local distributor.



Wright Medical Technology, Inc.
1023 Cherry Road
Memphis, TN 38117
U.S.A.



Tornier SAS
161 Rue Lavoisier
38330 Montbonnot Saint Martin
France

* The CE-Marking of Conformity is applied per catalog number and appears on the outer label, if applicable.



June 2018
Printed in U.S.A.

PRO-DENSE™ Bone Graft Substitute

(150844-2)

NOTE: Do not add any additional substances to the graft. Using alternative mixing solutions and/or adding other substances to the mixture may alter the safety and effectiveness of this product. Some substances, such as bone marrow and blood, will prevent the graft from setting.

NOTE: Do not attempt to bend the needle in this kit.

Preparation of Implant Site and Accessories

1. Pre-place needle in defect under fluoroscopic guidance.
2. Remove top from mixer and add all powder and solution.



3. Replace top and attach vacuum hose to the vacuum port. (Optional)



- 4a. **MIX** approximately 50 revolutions in 30 seconds (in one direction).



- 4b. **STOP** mixing and wait approximately 30 seconds before starting step 4c



- 4c. **MIX** approximately 25 revolutions in 15 seconds (in one direction).

Note: Inject paste in 3-5 min.



5. Disconnect vacuum hose (if connected), remove top, and scrape excess.



6. Remove red tab and rotate white base counterclockwise to expose syringe port.



7. Holding the mixer on its side, insert threaded extruder at an angle until completely seated and advance threaded extruder until graft just begins to enter syringe port as shown.



8. Press fit syringe barrel in vertical orientation. While gripping the clear chamber continue rotating/advancing extruder until syringe is filled.



9. Disconnect syringe.



10. Dock syringe to pre-placed needle. Begin injecting with steady thumb pressure. Avoid overfilling or pressurizing the treatment site.



Note: The graft will set in ~ 20 – 30 min.

NOTE: Residual material may be left in syringe. The amount of remaining material is relative to user's adherence to the mixing and ejecting times outlined in these instructions.

CAUTION: The paste should be allowed to set prior to definitive hardware placement. Do not disturb while curing.